

PPG RAVEN® 405 Epoxy

DESCRIPTION

100% solids epoxy coating for use as a corrosion protection and structural enhancement lining system

PRINCIPAL CHARACTERISTICS

- 100% solids
- Near zero VOCs (< 3 g/l)
- Ultra-high build characteristics
- Excellent chemical resistance
- Bonds to dry and damp concrete, masonry, steel, ductile iron and fiberglass
- Acceptable for both new and existing structures
- TYPICAL USES:
- Wastewater structures, buried pipelines, tanks, and other corrosive environments

Note: Information Sheet available with test and certification data

COLOR AND GLOSS LEVEL

- Light blue
- Part A is White, Part B is Blue; Mixed product is Light Blue
- Semi-gloss

Note: Color changes can occur under UV-exposure without negative impact on the product performance

BASIC DATA AT 72°F (22°C)

Data for mixed product	
Number of components	Two
Mass density	10.1 lb/US gal (1.2 kg/l)
Volume solids	100 ± 2%
VOC (Supplied)	EPA Method 24: 0.0 lb/US gal (0.5 g/l)
Recommended dry film thickness	30.0 - 250.0 mils (762 - 6350 µm) per coat
Theoretical spreading rate	54 ft ² /US gal for 30.0 mils (1.3 m ² /l for 750 µm) 6 ft ² /US gal for 250.0 mils (0.2 m ² /l for 6250 µm)
Dry to touch	3.5 hours
Overcoating Interval	Minimum: Coating should no longer leave residue when touched with a gloved finger Maximum: 12 hours



PPG RAVEN® 405 Epoxy

Data for mixed product

Curing time	5 hours
-------------	---------

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- If overcoat time is exceeded, abrade and clean surface before recoating
- Curing time reflects ready for service time
- The shelf life for the unmixed components (Part A and Part B) for this product is 24 months at 70°F (21°C).
- Material should be stored in dry conditions, out of direct sunlight, and in unopened original factory containers, at temperatures above 60°F (16°C) and below 100°F (38°C)

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Steel (Immersion Service)

- Remove all surface contaminants, oil and grease in accordance with SSPC SP-1
- Abrasive blast with an angular abrasive to an SSPC SP-10 cleanliness or higher. Achieve a surface profile of 3.0 – 5.0 mils (75 – 125 µm)
- Ensure surface is dust free after blasting
- Contact PPG for maximum allowable salt containment levels

Steel (Non-Immersion Service)

- Remove all surface contaminants, oil and grease in accordance with SSPC SP-1
- Abrasive blast with an angular abrasive to an SSPC SP-6 or higher. Achieve a surface profile of 2.5 – 4.0 mils (65 – 100 µm)
- Ensure surface is dust free after blasting
- Contact PPG for maximum allowable salt containment levels

Concrete / Masonry

- Surface must be sound and free from contamination (such as oil, grease, rust, scale, or deposits).
- Abrade surface to achieve a surface profile equivalent to CSP 3 to CSP 5 in accordance with ICRI 310.2R-2013
- Prepare in accordance with SSPC SP-13 guidelines

Ductile Iron

- All oils, small deposits of asphalt paint, and grease shall be removed by solvent cleaning per NAPF 500-03-01
- Abrasive blast in accordance with NAPF 500-03-04

Substrate temperature and application conditions

- Substrate temperature during application should be between 40°F (5°C) and 120°F (49°C)
- Substrate temperature during application and curing should be at least 5°F (3°C) above dew point

Note: For best results in limiting outgassing, apply to prepared concrete when the substrate temperature is stable or falling



PPG RAVEN® 405 Epoxy

SYSTEM SPECIFICATION

- Primers for concrete (optional): PPG RAVEN® 175 Primer, PPG RAVEN® 171FS Primer, PPG RAVEN® 155 Primer
- Primer for Carbon Steel: PPG AQUATAPOXY® 190 Primer*
- Primer for non-ferrous metals: PPG AQUATAPOXY® 190 Primer*
- Recommended DFT for New/Smooth Concrete: 80-250 mils (2030-6350 µm)
- Recommended DFT for Rough Concrete: 100-250 mils (2540-6350 µm)
- Recommended DFT for Resurfaced Concrete: 80-250 mils (2030-6350 µm)
- Recommended DFT for Masonry/Brick: 125-250 mils (3175-6350 µm)
- Recommended DFT for Resurfaced Masonry/Brick: 80-250 mils (2030-6350 µm)
- Recommended DFT for Steel (Carbon): 30-80 mils (762-2030 µm)
- Recommended DFT for Non-Ferrous Metals: 30-80 mils (762-2030 µm)

Note: *Do not use this primer if immersion temperatures will exceed 140°F (60°C)

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 75:25 (3:1)

- Application with twin-feed hot airless spray equipment

Notes:

- Do not thin with solvents.
- If lower viscosity is needed, heat unmixed material by placing the containers in hot tap water until the desired flow properties are obtained
- Do not heat unmixed material above 150°F (66°C)

Pot life

20 minutes at 72°F (22°C)

Notes:

- Listed pot life is for one US gallon quantity
- Longer pot life is possible by mixing smaller amounts and cooling down the components before mixing

Material temperature

Material temperature during application should be between 125°F (52°C) and 145°F (63°C) at gun

PPG RAVEN® 405 Epoxy

Airless spray: Plural component

- 3:1 Heated Plural Component Spray system is recommended
- 5:1 or 10:1 transfer pumps
- Heated hoses are recommended
- Achieve 2,000 - 3,000 psi
- Use 1/2" x 3/8", 24-element static wand mixer
- Pot life at whip/gun: 1-2 minutes
- Recommended tip size: 531-535
- Supply pump pressure: 100 psi (0.689 MPa)

Recommended thinner

No thinner should be added

Nozzle orifice

Approx. 0.031 in – 0.035 in (0.78 – 0.89 mm)

Nozzle pressure

1800 - 3000 p.s.i. (approx. 124 - 207 bar; 12.4 - 20.7 MPa)

Notes:

- Part A should be maintained at temperature range of 115-145°F (46-62°C)
- Part A should be 20°F (11°C) warmer than Part B during processing
- Part B should be maintained at temperature range of 90-125°F (32-52°C)

Trowel / Brush

- Product may be applied by brush or trowel by mixing small quantities and applying immediately
- For touch-up or holiday repair only
- HAND MIX INSTRUCTIONS:
- Individually power mix both the Part A and Part B components separately to ensure uniformity
- Measure out 3 parts of Part A to 1 part of Part B by volume into a clean disposable pail
- Completely mix combined A & B for a minimum of one minute before transferring contents to a clean pail.
- Continue mixing for at least another minute, scraping the sides and bottom, to obtain a thorough mix.
- Properly mixed material will be a uniform color without light or dark spots.

Cleaning solvent

MEK, acetone or xylene

PPG RAVEN® 405 Epoxy

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
30.0 mils (762 µm)	53 ft ² /US gal (1.3 m ² /l)
80.0 mils (2032 µm)	20 ft ² /US gal (0.5 m ² /l)
100.0 mils (2540 µm)	16 ft ² /US gal (0.4 m ² /l)
125.0 mils (3175 µm)	13 ft ² /US gal (0.3 m ² /l)
250.0 mils (6350 µm)	6 ft ² /US gal (0.2 m ² /l)

Physical data of cured material	
Characteristic	Value
Tensile Strength (ASTM D638)	>9,000 psi (>62.0 MPa)
Tensile Elongation (ASTM D638)	>6%
Compressive Strength (ASTM D695)	>18,000 psi (>124.1 MPa)
Flexural Strength (ASTM D790)	>15,000 psi (>103.4 MPa)
Hardness, Shore D (ASTM D2240)	87
Taber Abrasion (ASTM D4060, CS-17 Wheel, 1 kg load, 1,000 cycles)	57 mg loss
Adhesion to Concrete (ASTM D7234)	To substrate failure

Note: The value ranges stated in this Technical Data Sheet are based on system processing under laboratory conditions. Equipment configurations and/or field application conditions may produce variances in final system values.

DISCLAIMER

- PPG Protective & Marine Coatings does not accept any responsibility or liability for any odor, taste or contamination imparted to the drinking water from the coatings or products retained in the coating
- For industrial or professional use only
- This product is specifically suitable for use on the substrates mentioned in this document. For application on any other substrates, please always contact your distributor for specific instructions and in order to make sure that the product performance can be safeguarded.

SAFETY PRECAUTIONS

- Read all label and Safety Data Sheet (SDS) information prior to use



PPG RAVEN® 405 Epoxy

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
• SURFACE PREPARATION OF CONCRETE (FLOORS)	INFORMATION SHEET	1496

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

