



686 S. Adams Street
Kansas City, KS 66105
(913) 321-9000

AquataPoxy A-61

Technical Data Sheet

Selection & Specification Data

Description

AquataPoxy® A-61 is a solvent-free, 100% solids, high build epoxy coating. Formulated for single coat applications, A-61 is certified safe for cold potable water with a 5 hour cure to service time.

Typical Uses

Formulated for use on surfaces where corrosion and water resistance is needed, including:

- Potable water treatment structures
- Water distribution and transmission lines 30" and larger
- Tanks, reservoirs and basins

Color & Stability (Limitations)

The standard Part A Resin is white; the Part B Curing Agent is green. When mixed the product is aqua. The Part B is also available in a translucent brown, when used with white Part A; the mixed product is a white color.

While the physical properties may not be affected, epoxy coatings will fade or chalk with exposure to UV light or mercury vapor light.

Theoretical Coverage Rates

The theoretical coverage is 1604 sq. ft. per gallon at 1 mil dft. Actual surface coverage will depend on the substrate porosity and roughness of the substrate. Depending on substrate type and profile, a maximum of 120 mils is recommended to prevent sagging. Typical recommended thickness for immersion duty is 25-80 mils on metal and 60-120 mils on concrete.

Recommended Dry Film Thickness (Typical)

Carbon Steel (Atmospheric):	25– 40 mils DFT
Carbon Steel (Immersion):	26 - 80 mils DFT
Non-Ferrous Metal:	8 - 18 mils DFT
Ductile Iron:	20 - 24+ mils DFT
Concrete:	60 - 120+ mils DFT

Physical Properties (Typical) (Post cured at 225°F for 24 hours)

Description	Method	Result
Tensile Strength	ASTM D 638	7,700 psi
Tensile Elongation	ASTM D 638	1.2%
Compressive Strength	ASTM D 695	16.600 psi
Flexural Strength	ASTM D 790	10,600 psi
Hardness, Shore D	ASTM D 2240	88
Taber Abrasion CS-17 wheel	ASTM D 4060, 1 kg load/1,000 cycles	<111 mg loss
Adhesion, Steel	ASTM D 4541	>2,000 psi
Adhesion, Concrete	ASTM D 7234	Substrate Failure

The value ranges stated in this Technical Data Sheet are based on system processing under controlled laboratory conditions. Equipment configuration and/or field application conditions may produce variances in the final system values.

CERTIFICATIONS

Potable Water: AquataPoxy A-6 and A-6 Thick are certified to the requirements of ANSI/NSF 61 - Drinking Water System Components.

AWWA: AquataPoxy A-6 and A-6 Thick meet the physical and performance requirements of ANSI/AWWA C 210, "Liquid Epoxy Coating Systems for the Interior and Exterior of Steel Water Pipelines".



AquataPoxy A-61

Technical Data Sheet

Surface Preparation

General

Before coating, the substrate must be prepared in a manner that provides a uniform, clean, sound, neutralized surface suitable for the specified coating. The substrate must be free of all contaminants, such as oil, grease, rust, scale or deposits. In general, coating performance is proportional to the degree of surface preparation.

Steel, Immersion Service

Visible deposits of oil, grease, or other contaminants shall be removed according to SSPC-SP 1 Solvent Cleaning followed by SSPC-SP10/NACE No. 2 Near- White Metal Blast Cleaning, resulting in a sharp angular anchor profile of 2.5-5.0 mils.

Steel, Atmospheric/Non-Immersion Service

Visible deposits of oil, grease, or other contaminants shall be removed according to SSPC-SP 1 followed by SSPC-SP6/NACE No. 3 Commercial Blast Cleaning, resulting in a sharp angular anchor profile of 2.5-4.0 mils.

Ductile Iron Pipe, Atmospheric and Immersion Service

All oils, small deposits of asphalt paint and grease shall be removed by solvent cleaning (see NAPF 500-03-01). Abrasive blast to meet NAPF 500-03-04.

Concrete and Masonry Surfaces

Reference SSPC-SP 13/NACE No. 6 Surface Preparation of Concrete. Minimum surface profile equivalent to ICRI CSP3 to CSP5 in accordance with ICRI Technical Guideline 310.2R-13

Primers (Suggested)

Concrete (optional)	Raven 175**
	Raven 171FS**
	Raven 155**
Carbon Steel (blast holding)	AquataPoxy 190*

Priming PVC, PE, PP, PS, & HDPE- Contact Raven Tech Service

*Do not use this primer if immersion temperatures will exceed 140°F

**Penetrating primer for limiting outgassing.

Thinning Instructions and Pot Life

Power Mixing (Non-spray application)

Individually mix both Part A and Part B containers prior to measuring out 3 parts of Part A to 1 part of Part B by volume into a clean disposable pail. Completely mix combined A & B for a minimum of one minute before transferring contents to a clean pail. Continue mixing at least another minute, scraping the sides and bottom, to obtain a thorough mix before application. Properly mixed material will be a uniform color without light or dark spots.

Thinning

Do not reduce.

Pot Life

The pot life is 20 minutes at 72°F. Longer pot life is possible by mixing smaller amounts and/or cooling down the part A & B before mixing.



AquataPoxy A-61

Technical Data Sheet

Application Equipment & Conditions

Spray Application

Optimal proportioning and mixing is achieved with the use of a Raven Lining Systems approved plural-component airless spray system. Raven recommends the use of fixed ratio (3:1), such as, Graco XP 50 or 70 Plural-Component Pump System. Viscon Fluid Heaters and heated hoses are recommended. Carefully monitor, heating devices such as drum blankets or bands to avoid scorching of the material or melting drum liners. Pre-heating containers must not exceed temperatures greater than 150°F.

Spray Equipment Set-up (Typical)

A-Side Temp	125-135°F
B-Side Temp	110-115°F
Hose Heat	140°
Tip Size	525-531
Fluid Pressure @ Pump	2800-3000 psi
Fluid Pressure @ Block	2700-2800 psi
A-Side Hose diameter	1/2"
B-Side Hose diameter	3/8"
Pot life at Whip/Gun	1-2 minutes

Application Conditions:

Temperature: 50°F Minimum, 120°F Maximum (Air and Surface). At least 5°F above dew point. Relative Humidity <85% maximum.

Curing & Re-Coat Window

Cure Time

Thin film set time varies with substrate temperature and application thickness. Generally, the coating will be tack-free in 3 hours at 72°F and dry-hard in about 4½ hours. This product is designed for single coat applications.

Cure to Service (ANSI/NSF Standard 61)

5 hours at 72°F

Recoat Time

This product has no recoat window. If a second coat or repair is required, visually inspect, clean and dry surface thoroughly to remove all contamination, including amine blush or condensation. Abrade the surface before recoating to create a clean, rough, dull, and dry surface.

Packaging, Handling, & Storage

Packaging:

Available in Gallon, 20-Gallon, 120-Gallon, and 220-Gallon kits. Kits are supplied in the correct proportions of A & B; the two components must be mixed together before use.

Shelf Life:

The product can be stored for one year in factory delivered, unopened containers. Keep away from extreme heat, freezing, and moisture.

Storage Temperature & Humidity

Store in a sheltered area between 50°F (10°C) and 100°F (37°C).



AquataPoxy A-61

Technical Data Sheet

Cleanup & Safety

Cleanup

Cured product may be disposed of without restriction. The un-cured portions should be mixed together and disposed of in a normal manner. Preferred cleaning solvents are MEK, Xylene, or Acetone. "Drip free" containers should be disposed of according to state, local, and federal laws.

Safety

SDS's are available on the website, (www.ravenlining.com) or upon request. Consult the Safety Data Sheet for this product concerning health and safety information before using. Strictly follow all notices on the Safety Data Sheet and container label. If you do not fully understand the notices and procedures provided on the SDS or if you cannot strictly comply with them, do not use this product. Actual safety measures are dependent on application methods and work environment. Keep uncured product away from children at all times.

Warranty

Limited Warranty. Company warrants its goods to be free of manufacturing defects. Goods manufactured by Company will comply with all applicable federal, state and local laws and regulations. Company makes no warranty as to any parts or equipment manufactured by others. Customer shall look solely and only to the manufacturer of such parts or equipment with respect to any warranty claims. Company hereby assigns to Customer the original manufacturer's warranties to all such equipment and parts, to the full extent permitted. THE AFORESAID IS THE EXCLUSIVE WARRANTY AND IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED. SPECIFICALLY, THERE ARE NO WARRANTIES OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE.

Limitation of Liability. COMPANY'S LIABILITY FOR DEFECTIVE OR NON-CONFORMING GOODS SHALL BE LIMITED TO, AND SHALL IN NO EVENT EXCEED, THE AMOUNT PAID BY CUSTOMER FOR SUCH DEFECTIVE OR NON-CONFORMING GOODS. UNDER NO CIRCUMSTANCES SHALL COMPANY BE LIABLE FOR ANY SPECIAL, PUNITIVE, INCIDENTAL OR CONSEQUENTIAL DAMAGES OR FOR LOST PROFITS. In no event may any claim by Customer arising from or relating to any sale of any goods or services referenced herein be brought more than one year after the date of delivery of such Goods.